



# Product Specification Document

ACAD-480-900MM/TA Rev 2

Aluminum Coil Anodizing Corporation  
 501 E. Lake Street • Streamwood, IL 60107  
 Phone: 630-837-4000 • Fax: 630-837-0814  
 www.acacorp.com

**Product ID: 480-900MM/TA Tannenbaum Medium Etch**

**Application: Lighting Reflectors, Typically Short Cross-Blades or Large Back Reflectors**

<b>Material Specification:</b>			
Alloy:	3105		
Temper:	H24		
Mechanical Properties (typical):			
Tensile Strength:	170 N/mm <sup>2</sup>	(25,000 psi)	For White Paint: 1T bend: n/a 1T bend – dry heat: n/a 0T bend: n/a
Yield Strength:	160 N/mm <sup>2</sup>	(23,000 psi)	
Elongation:	8%		
Minimum Bend Radii:	n/a		

<b>Optical / Anodized Properties:</b>			
Total Reflectance (TR%) <sup>1</sup> :	72% minimum		<sup>1</sup> (Technidyne TR-2 (ASTM 1651-94))
Distinctness of Image (DI) <sup>2</sup> :	n/a		<sup>2</sup> (Hunter Labs D47 Dorigon (ASTM E430-83))
Specular Reflectance (RS) <sup>2</sup> :	n/a		<sup>3</sup> (DIN 67530)
15° Diffuseness (15°) <sup>2</sup> :	n/a		<sup>4</sup> (Byk Gardner Micro Gloss Meter)
Dr. Lange 60° <sup>3</sup> :	w/g	n/a	a/g n/a
Gardner 60° Gloss <sup>4</sup> :	w/g	15 to 35	a/g n/a
Anodize Film Thickness <sup>5</sup> :	2.5 to 3.8 microns (0.0001 to 0.00015 inch)		
Iridescence Rating:	Controlled Low Iridescence		
Color <sup>6</sup> :	L*	n/a	a* n/a b* n/a

<b>Availability:</b>	Sheet and Coil		
Gage:	0.30 to 0.80 mm	(0.012 to 0.032 inch)	
Width:	25.4 to 610 mm	(1.0 to 24.0 inch)	
Length:	up to 3660 mm	(up to 144 inch)	

<b>Tolerances (standard):</b> (Tighter tolerance may be possible. Contact your sales representative.)				
Gage:	From:	0.25 to 0.40 mm	+/- 0.025 mm	(0.010 to 0.016 inch, +/- 0.001 inch)
		0.41 to 0.80 mm	+/- 0.040 mm	(0.017 to 0.032 inch, +/- 0.0015 inch)
		0.81 to 1.00 mm	+/- 0.050 mm	(0.033 to 0.040 inch, +/- 0.002 inch)
Slit Width:	From:	12.5 to 305 mm	+/- 0.125 mm	(0.5 to 12 inch, +/- 0.005 inch)
		306 to 610 mm	+/- 0.38 mm	(12.1 to 24 inch, +/- 0.015 inch)
		611 to 1250 mm	+/- 0.50 mm	(24.1 to 50 inch, +/- 0.020 inch)
Sheet:	Length:	Up to 1524 mm	+/- 1.0 mm	(Up to 60 inch, +/- 0.040 inch)
		1525 to 3050 mm	+/- 1.5 mm	(60 to 120 inch, +/- 0.060 inch)
		3051 to 3660 mm	+/- 2.0 mm	(120 to 144 inch, +/- 0.080 inch)
	Squareness: <sup>1</sup>	Up to 1200 mm	+/- 0.5 mm	(Up to 48 inch, +/- 0.020 inch)
		1201 to 2400 mm	+/- 1.0 mm	(49 to 95 inch, +/- 0.040 inch)
		2401 to 3660 mm	+/- 1.5 mm	(96 to 144 inch, +/- 0.060 inch)
<sup>1</sup> Difference in diagonals				
Lateral Bow (in one meter):	For normal widths 25-75 mm: 1 mm max (For normal widths 1-3 in: .040 in max)			
Flatness:	Height between waves: 1% of wave length, 8mm (0.32 inch) maximum.			
Burr:	10% of gage Not to exceed .08 mm (.003 inch)			